BPCL: NRMB

(Natural Rubber Modified Bitumen)

SN.	PARAMETER	METHOD	SPECIFICATION
1	Ductility @ 27 °C, cm	IS 1208	Min 50
2	Elastic Recovery of half thread @ 15°C, %	ASTM D 5976	Min 35
3	Flash Point (COC), °C	IS 1209	Min 220
4	Penetration @ 25°C, 100g, 5s, 1/10th of mm	IS 1203	Min 50, Max 89
5	Softening Point (R&B), °C	IS 1205	To Report

Remarks : Product conforms to Refinery specifications

The above specifications may vary as per the agreement with the customer. Please contact us for more details.